

FIG. 2




FIG.3a




FIG. 3b





FIG. 4a



CHARGER

FIG. 4b




FIG. 6a





FIG. 6b







Fig.7





parper n. T. a substance made from cellulese fibres derived from rags wood, etc., often with other additives and formed into flat thin sheets suitable for withing on decorating walls are 2 sections size at such

Fig12

This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

| _ | refeets in the images metade out are not immitted to the items encoded. |
|---|---|
| | ☐ BLACK BORDERS |
| | ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES |
| | ☐ FADED TEXT OR DRAWING |
| | ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING |
| | ☐ SKEWED/SLANTED IMAGES |
| | ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS |
| | ☐ GRAY SCALE DOCUMENTS |
| | ☐ LINES OR MARKS ON ORIGINAL DOCUMENT |
| | REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY |
| | I . |

IMAGES ARE BEST AVAILABLE COPY.

OTHER:

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.